

CHEMICAL ANALYSIS OF MAIN SOUTH AMERICAN ULEXITE SOURCES

In the tests below, all samples were of similar particle size.

	TOTAL B% <i>(guaranteed)</i>	% B SOLUBLE IN HOT H ₂ O	HEAVY METAL ARSENIC (PPM)
 GRANUBOR®	15%	100%	4
Ulexite (Bolivia) <i>calcinated in Brazil</i>	10%	44%	51
Ulexite (Peru)	10%	59%	962
	15%	26.6%	41
Ulexite (Argentina)	10%	35%	96
	15%	23.3%	105
Ulexite (Chile)	10%	22%	4,214

(analysis performed by U.S. Borax)